


MARKANT

Ancora

Specsheet



Ancora specsheet

Construction details

Fabric Quality	ANCORA NTH
Composition	100% Harmolan PP
Density	warp: 9 thr./cm weft: 6 thr./cm
Weight g/m²	390 g
Weight g/Lm	538 g
Width	138 cm
Custom tariff	54077300

Cleaning instructions



Test Results

Abrasion Resistance EN ISO 12947-2			45 000 T
Seam Slippage EN ISO 13936-2	warp:	5 mm	
	weft:	4 mm	
Tensile Strenght EN ISO 13934-1	warp:	905 N	
	weft:	2100 N	
Tearing Strenght EN ISO 13937-3	warp:	99 N	
	weft:	310 N	
Colour fastness to rubbing EN ISO 105-X12	dry:	note:	4-5
	wet:	note:	4-5
Colour fastness to light EN ISO 105-B02		note:	≥ 5
Pilling Resistance EN ISO 12945-2		note:	≥ 4

Ancora specsheet

Colors

